


STÄRKEN

**Drymix
Solutions**

TM



Tile Adhesive Series

DURA BOND 362

**C2TE CLASS TILE ADHESIVE
FOR LARGE CERAMIC AND
PORCELAIN TILES**

**High-performance tile adhesive complying
C2TE class of EN 12004 for large size
ceramic, homogeneous and porcelain tiles**

Uses

- Suitable for interior and exterior, wet and dry areas
- Wall and floor thin bed tiling
- For ceramic, porcelain and homogeneous tiles
- Tiling on concrete, render and screed

Benefits

- High adhesive strength
- Extended open time
- Slip resistance

www.starkendrymix.com.my

Tile Adhesive Series

DURA BOND 362

C2TE CLASS TILE ADHESIVE FOR LARGE CERAMIC AND PORCELAIN TILES



TECHNICAL PROPERTIES

Initial Tensile Adhesion Strength	≥ 1.0 N/mm ²
Tensile Adhesion Strength After Water Immersion	≥ 1.0 N/mm ²
Tensile Adhesion Strength After Heat Ageing	≥ 1.0 N/mm ²
Open Time	≥ 30 mins
Slip Resistance	≤ 0.5 mm

PHYSICAL FEATURES

Package	25 kg and 40 kg
Water Demand	5.5 - 6.5 ℓ / 25 kg bag 8.8 - 10.4 ℓ / 40 kg bag
Consumption	1.3 kg/m ² /mm
Filler Size	< 2.0 mm
Pot Life	Approx. 2 hours

RECOMMENDED THICKNESS

Tile Size	Bedding Thickness
≤ 300 mm x 300 mm	3 - 8 mm
≤ 600 mm x 600 mm	6 - 10 mm
> 600 mm x 600 mm	8 - 12 mm

STORAGE

Shelf life is 6 months if stored in dry and cool place

Starken Drymix Solutions Sdn. Bhd.

201001032580 (916505-X)

Menara Chin Hin
Level 22-23, 8th & Stellar,
No. 1, Jalan Naga Emas, Sri Petaling,
57000 Kuala Lumpur, Malaysia

T: +603-7982 8066

STÄRKEN Drymix Solutions

TM

APPLICATION

SUBSTRATE PREPARATION

- 1 All surfaces must be structurally sound, clean and free from mould oil, grease, loose particles and contamination of foreign materials

APPLICATION PROCEDURE

- 1 Mix 1 bag of 25 kg **Dura Bond 362** with 5.5 – 6.5 litres of water or 8.8 - 10.4 litres of water for 40 kg bag using electrical mixer for at least 3 minutes until homogeneous mixture is achieved
- 2 Spread the adhesive using a suitable notched trowel directly onto the substrate with area not more than 1 m² to prevent premature drying (skin-over formation)
- 3 Press tile firmly onto adhesive bed with a slight twisting motion to ensure good contact between the tile and adhesive
- 4 Unfavourable weather conditions, such as strong sunlight, wind, temperature, humidity, or highly absorbent substrate can reduce the open time
- 5 Once the adhesive surface dries to the touch, remove it and apply a fresh layer of adhesive. Avoid re-wetting the surface with water, as this can create a weak, non-adhesive film
- 6 Adjust tile alignment within 10 minutes
- 7 Tile Grout **Fine Fill 302** should be applied at least 24 hours after tiling

For detailed instructions on the procedure, please refer to our Method Statement.

CURING

- 1 Natural air curing is sufficient

HEALTH & SAFETY

- 1 Wear protective gloves/ protective clothing/ eye protection/face protection.
- 2 In case of contact with eyes or skin, rinse immediately with water and seek medical advice if needed.
- 3 For complete information about the safe use of our product, please refer to the latest version of Safety Data Sheet.

Disclaimer:

The information provided in this data sheet has been carefully compiled using the most current references available. However, no warranty, guarantee, or representation is made regarding its accuracy, reliability, or completeness. Users are responsible for evaluating the suitability and adequacy of this information for their specific needs. We shall not be held liable for any loss or damage arising from the use of this information. This data sheet is subject to change or modification without prior notice as part of our ongoing product development.